



TECHNICAL REPORT
NATICK/TR-91/039

AD _____

AD-A286 512
|||||

MODIFICATION OF THE NEAR-IR REFLECTANCE REQUIREMENTS TEST

By
ROBERT A. PROSSER
LISA B. HEPFINGER

June 1991

Final Report
October 1989 - September 1990

DTIC
ELECTE
NOV 28 1994
S B D

APPROVED FOR PUBLIC RELEASE;
DISTRIBUTION UNLIMITED

DTIC QUALITY INSPECTED 5

UNITED STATES ARMY NATICK
RESEARCH, DEVELOPMENT AND ENGINEERING CENTER
NATICK, MASSACHUSETTS 01760-5000

INDIVIDUAL PROTECTION DIRECTORATE

94-36208

|||||

94 11 28 00 2

DISCLAIMERS

The findings contained in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Citation of trade names in this report does not constitute an official endorsement or approval of the use of such items.

DESTRUCTION NOTICE

For Classified Documents:

Follow the procedures in DoD 5200.22-M, Industrial Security Manual, Section 11-19 or DoD 5200.1-R, Information Security Program Regulation, Chapter IX.

For Unclassified/Limited Distribution Documents:

Destroy by any method that prevents disclosure of contents or reconstruction of the document.

| REPORT DOCUMENTATION PAGE | | | Form Approved OMB No. 0704-0188 | |
|--|---|---|------------------------------------|--|
| <small>Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.</small> | | | | |
| 1. AGENCY USE ONLY (Leave blank) | 2. REPORT DATE June 1991 | 3. REPORT TYPE AND DATES COVERED Final Oct. 89 - Sept. 90 | | |
| 4. TITLE AND SUBTITLE Modification of the Near-IR Reflectance Requirements Test | | 5. FUNDING NUMBERS FE IL162786 PR - NID8 PR - T/B 1168 | | |
| 6. AUTHOR(S) Robert A. Prosser and Lisa B. Heflinger | | | | |
| 7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) U.S. Army Natick Research, Development, and Engineering Center Attn: STENC-ITC Natick, MA 01760-5019 | | 8. PERFORMING ORGANIZATION REPORT NUMBER NATICK/TR-91/039 | | |
| 9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) | | 10. SPONSORING/MONITORING AGENCY REPORT NUMBER | | |
| 11. SUPPLEMENTARY NOTES IPD - 450 | | | | |
| 12a. DISTRIBUTION/AVAILABILITY STATEMENT Approved for Public Release; Distribution Unlimited | | | 12b. DISTRIBUTION CODE | |
| 13. ABSTRACT (Maximum 200 words) <p>By choosing dyes for the US Army's Woodland Battledress Uniform (BDU) colors which provide spectral reflectance values compatible with those of the major components of a verdant terrain during the day and night, the BDU blends better with the environment during the day and does not present a readily detectable monotone when viewed through a starlight scope. Thus, camouflage has been extended into the near-IR.</p> <p>On occasion, dyers have had difficulty in meeting both the visual and NIR requirements. This report describes a method of acceptability testing requiring only a single (pass/fail) value. This value is obtained using an integration procedure over the wavelengths of interest instead of requiring that the reflectance values fall within a specified band. The test should make it easier for the dyed or printed material to meet the production specification requirements, and still provide the necessary reflectance properties for effective camouflage in the near-IR.</p> | | | | |
| 14. SUBJECT TERMS WOODLAND CAMOUFLAGE TEST AND EVALUATION VISUAL REQUIREMENTS ACCEPTABILITY NEAR INFRARED REFLECTANCE FABRIC DYES NIGHT | | | 15. NUMBER OF PAGES 24 | |
| | | | 16. PRICE CODE | |
| 17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED | 18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED | 19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED | 20. LIMITATION OF ABSTRACT SAR | |

SUMMARY

By choosing dyes for the US Army's Woodland Battledress (BDU) colors which provide spectral reflectance values compatible with those of the major components of a verdant terrain during the day and night, the BDU blends better with the environment during the day and does not present a readily detectable monotone when viewed through a starlight scope. Thus, camouflage has been extended into the near-IR (NIR).

On occasion, dyers have had difficulty in meeting both the visual and NIR requirements. This report describes a method of acceptability testing requiring only a single (pass/fail) value. This value is obtained using an integration procedure over the wavelengths of interest instead of requiring that the reflectance values fall within a specified band. The test should make it easier for the dyed or printed material to meet the production specification requirements, and still provide the necessary reflectance properties for effective camouflage in the NIR.

| | |
|---------------|-------------------------------------|
| Accession For | |
| NTIS GRA&I | <input checked="" type="checkbox"/> |
| DTIC TAB | <input type="checkbox"/> |
| Unannounced | <input type="checkbox"/> |
| Justification | |
| By | |
| Distribution | |
| Availability | |
| Special | |
| Dist | |
| A-1 | |

Table of Contents

| | |
|-----------------------------|-----|
| Summary | iii |
| List of Figures and Tables | vii |
| Preface and Acknowledgement | ix |
| Introduction | 1 |
| Procedure | 1 |
| Discussion and Results | 2 |
| Conclusion | 10 |
| References | 11 |
| Appendix | 12 |

List of Figures and Tables

| Figure | Page |
|--|----------|
| 1. Ls Values for Light Green 354 and Dark Green 355 | 13 |
| 2. Ls Values for Light Green 354 and Brown 356 | 14 |
| 3. Ls Values for Dark Green 355 and Brown 356 | 15 |
| 4. Night Vision Scope Sensitivities | 16 |
| Table | Page |
| 1. Statistical Values for Woodland Pattern Colors | 3 |
| 2. NIR Acceptability Channel Violations | 6 |
| 3. Total Channel Violations per Sample | 7 |
| 4. Number of Sample Failures Using Channel and Statistical Criteria | 8 |
| 5. Revised Ls Values for Pass/Fail Test | 10 |

Preface

This report describes a new and simpler acceptability test needed to determine whether or not near-IR criteria are met. The study was carried out by investigators from the U. S. Army Natick Research, Development and Engineering Center from October 1989 to September 1990.

Acknowledgement

The authors would like to thank Ms. T. Commerford and Mr. M. Larrivee of the U.S. Army Natick Research, Development, and Engineering Center for their advice and support during the course of this investigation.

Modification of the Near-IR Reflectance Requirements Test

Introduction

The need for camouflage in the near-IR (NIR) has been fully discussed by Ramsley & Yeomans (1). The current reflectance qualification procedure for the Woodland Battledress Uniform requires checking 14 reflectance values in the NIR, 600 - 860 nm (2). This report describes a simplification of their reflectance qualification procedure, and evaluates recent (unclassified) advances in night vision devices.

Briefly, there is sufficient light in the night sky (moonlit or moonless) to enable objects with reflectances substantially different from the surroundings to be seen quite clearly with image intensifiers such as the AN/PVS-2B Night Vision Sight. If a soldier's clothing has a very high or very low, and especially uniform, reflectance across the visible and NIR ranges compared to the background, he becomes an obvious target for a sniper using a starlight scope.

To avoid this situation, the dyes used to match each color must provide the required spectral matches from 400 to 900 nm, but have reflectances from 700 to 900 nm (NIR) which are substantially different from each other but still similar to various terrain elements. Thus, when the uniform is when viewed through a starlight scope, no longer presents a monotone target that is readily discernible, but, instead, appears as a patchwork of light and dark areas that blends with the surroundings.

Procedure

To provide different reflectances across the NIR, each camouflage color was assigned a bandwidth (2) in the NIR within which its reflectance spectrum should fall. Even though the bandwidth (channel) is usually greater than plus or minus 10% of the reflectance of the standard, dyers have had difficulty in obtaining formulations that meet the visual color specifications and also provide reflectances that fall entirely within the standard's NIR channel at night. Consequently, colors that trespassed the channel boundaries at 3 or fewer points were accepted, since this did not appreciably affect the NIR spectral reflectance requirements. However, a simpler method was desired that would provide a single number (pass/fail) criterion for acceptance and obviate waived buys.

Using the integration method developed by Ramsley and Yeomans, pass/fail limits for the test were obtained empirically. Reflectance data had been collected over a period of time on a large number of nylon/cotton twill samples of the following colors: Light Green 354, 1805 samples; Dark Green 355, 1833 samples; and Brown 356, 1742 samples. These data were then used to calculate the average value of N_s for nighttime illumination, and the corresponding value of L_s , the lightness under nighttime illumination, for both moonlit and moonless conditions.

The value of N_s , the nighttime illumination using the starlight scope, is given by the following equation (1):

$$N_s = \int_{400}^{900} I_x S_x R_x dx$$

where I_x = spectral power distribution of moonlight or night sky radiance,

S_x = spectral sensitivity of the sensor,

R_x = reflectance.

N_s is analogous to the tristimulus value, Y , and is, therefore, the correlate of lightness in the visible range. The equation for L_s is:

$$L_s = 116 (N_s/N_w)^{1/3} - 16$$

where N_w is the integrated reflectance of a perfect white. L_s and N_w are analogous to L^* and Y_n respectively in the visible range. (3)

Second and third generation night vision scopes with improved sensitivities, S_x , have become available (4). The sensitivity data used for the Foreign Night Vision scope is similar to that used by Ramsley and Yeomans.

Discussion and Results

The average values found for N_s and L_s and their statistical limits are given in Table 1 for all three scopes. A detailed accounting of the NIR failures (channel violations) for all three colors examined, Light Green 354, Dark Green 355, and Brown 356, are given in Tables 2 and 3.

Table 2 gives the number of channel violations at each wavelength. Examples are: For Light Green 354, 19 samples had reflectances exceeding the upper limit at 680 nm. For Dark Green 355, the reflectance values of 30 samples were lower than allowed at 740 nm. For Brown 356, the reflectance values of 99 samples were below the lower limit of the acceptability band at

Table 1. Statistical Values for Woodland Pattern Colors

Light Green 354

Foreign Night Vision Scope

| | Moonlit | | Moonless | |
|------------------|-----------|-----------|-----------|-----------|
| | <u>Ns</u> | <u>Is</u> | <u>Ns</u> | <u>Is</u> |
| Mean + 3 Std Dev | 20.5 | 52.8 | 27.0 | 59.3 |
| Mean + 2 Std Dev | 19.4 | 51.3 | 25.6 | 57.8 |
| Mean | 17.0 | 48.3 | 22.8 | 54.9 |
| Mean - 2 Std Dev | 14.7 | 45.3 | 20.1 | 52.0 |
| Mean - 3 Std Dev | 13.6 | 43.9 | 18.7 | 50.5 |

Second Generation Night Vision Scope

| | <u>Ns</u> | <u>Is</u> | <u>Ns</u> | <u>Is</u> |
|------------------|-----------|-----------|-----------|-----------|
| Mean + 3 Std Dev | 26.5 | 58.8 | 45.2 | 73.4 |
| Mean + 2 Std Dev | 25.0 | 57.3 | 42.9 | 71.6 |
| Mean | 22.2 | 54.2 | 38.2 | 68.2 |
| Mean - 2 Std Dev | 19.3 | 51.1 | 33.6 | 64.7 |
| Mean - 3 Std Dev | 17.8 | 49.5 | 31.2 | 62.9 |

Third Generation Night Vision Scope

| | <u>Ns</u> | <u>Is</u> | <u>Ns</u> | <u>Is</u> |
|------------------|-----------|-----------|-----------|-----------|
| Mean + 3 Std Dev | 33.2 | 64.6 | 50.7 | 76.8 |
| Mean + 2 Std Dev | 31.5 | 63.1 | 48.3 | 75.1 |
| Mean | 28.1 | 60.0 | 43.3 | 71.8 |
| Mean - 2 Std Dev | 24.8 | 56.9 | 38.4 | 68.4 |
| Mean - 3 Std Dev | 23.1 | 55.4 | 35.9 | 66.7 |

Table 1. Statistical Values for Woodland Pattern Colors, Cont'd.

Dark Green 355

Foreign Night Vision Scope

| | Moonlit | | Moonless | |
|------------------|-----------|-----------|-----------|-----------|
| | <u>Ns</u> | <u>Ls</u> | <u>Ns</u> | <u>Ls</u> |
| Mean + 3 Std Dev | 11.2 | 40.2 | 15.6 | 46.7 |
| Mean + 2 Std Dev | 10.5 | 38.9 | 14.8 | 45.4 |
| Mean | 9.2 | 36.2 | 13.0 | 42.7 |
| Mean - 2 Std Dev | 7.8 | 33.6 | 11.2 | 40.1 |
| Mean - 3 Std Dev | 7.1 | 32.3 | 10.4 | 38.8 |

Second Generation Night Vision Scope

| | <u>Ns</u> | <u>Ls</u> | <u>Ns</u> | <u>Ls</u> |
|------------------|-----------|-----------|-----------|-----------|
| Mean + 3 Std Dev | 14.5 | 45.1 | 26.2 | 58.6 |
| Mean + 2 Std Dev | 13.6 | 43.7 | 24.7 | 56.9 |
| Mean | 11.8 | 40.9 | 21.7 | 53.6 |
| Mean - 2 Std Dev | 10.1 | 38.1 | 18.6 | 50.3 |
| Mean - 3 Std Dev | 9.2 | 36.7 | 17.1 | 48.7 |

Third Generation Night Vision Scope

| | <u>Ns</u> | <u>Ls</u> | <u>Ns</u> | <u>Ls</u> |
|------------------|-----------|-----------|-----------|-----------|
| Mean + 3 Std Dev | 19.4 | 51.4 | 32.5 | 64.1 |
| Mean + 2 Std Dev | 18.3 | 50.0 | 30.7 | 62.4 |
| Mean | 16.1 | 47.1 | 27.2 | 59.1 |
| Mean - 2 Std Dev | 13.9 | 44.2 | 23.6 | 55.7 |
| Mean - 3 Std Dev | 12.8 | 42.8 | 21.8 | 54.1 |

Table 1, Statistical Values for Woodland Pattern Colors, Cont'd.

Brown 356

Foreign Night Vision Scope

| | Moonlit | | Moonless | |
|------------------|-----------|-----------|-----------|-----------|
| | <u>Ns</u> | <u>Is</u> | <u>Ns</u> | <u>Is</u> |
| Mean + 3 Std Dev | 10.0 | 38.1 | 14.9 | 45.9 |
| Mean + 2 Std Dev | 9.4 | 36.9 | 14.1 | 44.5 |
| Mean | 8.2 | 34.4 | 12.4 | 41.9 |
| Mean - 2 Std Dev | 7.0 | 31.9 | 10.8 | 39.2 |
| Mean - 3 Std Dev | 6.4 | 30.6 | 9.9 | 37.8 |

Second Generation Night Vision Scope

| | <u>Ns</u> | <u>Is</u> | <u>Ns</u> | <u>Is</u> |
|------------------|-----------|-----------|-----------|-----------|
| Mean + 3 Std Dev | 13.8 | 44.3 | 27.6 | 59.9 |
| Mean + 2 Std Dev | 13.0 | 42.9 | 26.0 | 58.2 |
| Mean | 11.3 | 40.1 | 22.7 | 54.7 |
| Mean - 2 Std Dev | 9.7 | 37.3 | 19.5 | 51.3 |
| Mean - 3 Std Dev | 8.8 | 35.9 | 17.9 | 49.5 |

Third Generation Night Vision Scope

| | <u>Ns</u> | <u>Is</u> | <u>Ns</u> | <u>Is</u> |
|------------------|-----------|-----------|-----------|-----------|
| Mean + 3 Std Dev | 19.2 | 51.3 | 33.4 | 64.9 |
| Mean + 2 Std Dev | 18.1 | 49.8 | 31.6 | 63.2 |
| Mean | 16.0 | 46.9 | 27.9 | 59.7 |
| Mean - 2 Std Dev | 13.8 | 43.9 | 24.2 | 56.3 |
| Mean - 3 Std Dev | 12.7 | 42.4 | 22.3 | 54.5 |

Table 2. NIR Acceptability Channel Violations

Total Samples Which Exceeded the Acceptability Limit at Each Wavelength

| | Nanometers | | | | | | | | | | | | | |
|-----------------|------------|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|
| | 600 | 620 | 640 | 660 | 680 | 700 | 720 | 740 | 760 | 780 | 800 | 820 | 840 | 860 |
| Light Green 354 | | | | | | | | | | | | | | |
| Too High | | | | | | | | | | | | | | |
| | 0 | 1 | 1 | 17 | 19 | 9 | 7 | 12 | 12 | 2 | 4 | 2 | 2 | 2 |
| Too Low | | | | | | | | | | | | | | |
| | 0 | 0 | 0 | 0 | 0 | 8 | 5 | 7 | 1 | 0 | 0 | 0 | 0 | 5 |
| Dark Green 355 | | | | | | | | | | | | | | |
| Too High | | | | | | | | | | | | | | |
| | 1 | 1 | 2 | 1 | 1 | 1 | 2 | 2 | 2 | 2 | 2 | 2 | 1 | 1 |
| Too Low | | | | | | | | | | | | | | |
| | 0 | 0 | 0 | 0 | 0 | 0 | 0 | 30 | 63 | 89 | 65 | 57 | 68 | 72 |
| Brown 356 | | | | | | | | | | | | | | |
| Too High | | | | | | | | | | | | | | |
| | 0 | 0 | 1 | 0 | 0 | 1 | 1 | 1 | 1 | 1 | 0 | 0 | 0 | 0 |
| Too Low | | | | | | | | | | | | | | |
| | 1 | 1 | 1 | 0 | 0 | 1 | 1 | 2 | 2 | 18 | 31 | 42 | 76 | 99 |

Table 3. Total Channel Violations Per Sample

Number of Samples with N Locations Exceeding the Acceptability Limits

N = 1 2 3 4 5 6 7 8 9 10 11 12 13 14

Light Green 354

Too High

12 13 2 3 4 0 2 0 0 0 0 0 0 0

Too Low

9 0 4 0 1 0 0 0 0 0 0 0 0 0

Dark Green 355

Too High

1 0 0 0 0 0 1 0 0 0 0 0 1 0

Too Low

19 18 6 3 12 23 23 0 0 0 0 0 0 0

Brown 356

Too High

0 0 0 0 0 1 0 0 0 0 0 0 0 0

Too Low

27 33 15 15 13 0 0 0 0 0 0 1 0 0

860 nm. Table 3 presents the same data from another point of view. Here the total number of failures per sample are tallied. Examples are: For Dark Green 355, there were 12 samples each with a total of 5 reflectances that were too low. For Brown 356, there were 33 samples that had a total of two failures: all had reflectances that were too low. As can be seen from Table 3, there were only two samples that had more than 7 failures. These were: Dark Green 355, N = 13, too high, and Brown 356, N = 12, too low. Table 3 also shows that out of 1805 samples for Light Green 354, nine had more than 3 violations that were too high, and one sample failed because its reflectance was too low at five wavelengths. For Dark Green one sample failed because there were 7 wavelengths at which the reflectance readings were above the upper limits, and 61 samples had more than 3 reflectance values which were beneath the lower limits. Finally, for Brown 356 one sample failed because it had more than 3 violations (all were too high), and twenty-nine samples had more than 3 violations (all were too low).

The number of samples that exceeded the assigned channel boundaries at 4 or more wavelengths (and were thereby rejected), and the number that failed using statistical criteria based on the third generation night vision scope under moonless conditions are given in Table 4. The third generation scope data were used because these devices respond almost equally under moonless as well as moonlit conditions.

Table 4. Number of Sample Failures Using
Channel and Statistical Criteria

| <u>Color</u> | <u>No. of Samples</u> | <u>Channel</u> | <u>2-Sigma</u> | <u>3-Sigma</u> |
|---------------|-----------------------|----------------|----------------|----------------|
| Lt. Green 354 | 1805 | 10 | 90 | 6 |
| Dk. Green 355 | 1833 | 63 | 92 | 6 |
| Brown 356 | 1742 | 30 | 87 | 5 |

Apparently, the easiest color to match, and also meet the NIR requirements, was the Light Green 354, since there were only 10 samples that failed at more than three wavelengths. It is evident from Table 2, that the upper limit of the acceptability channel from 660 to 760 nm was the troublesome region for Light Green 354. For both Dark Green 355 and Brown 356, the troublesome region was the lower limit from 740 or 780 to 860 nm.

Plots of the average value of I_s , the average plus and minus two standard deviations, and the average plus and minus three standard deviations, are given in Figures 1 to 3 where they are represented by an asterisk, plus sign, square, dot, and X respectively. Figure 1 compares the averages for Light Green 354 and Dark Green 355. Figure 2 compares the averages for Light Green 354 and Brown 356, and Figure 3 compares the averages for Dark Green 355 and Brown 356.

The averages for moonlit conditions are based on the assumption that the spectral power distribution of moonlight is the same as the spectral power distribution of the moonlit night sky and is equivalent to CIE source D5500 (1). The radiance of the moonless night sky, which, when normalized, appears relatively rich in infrared energy, has not been included in the moonlit calculations. This was done because the radiant energy in the visible and NIR under moonless conditions is small compared to the energy under moonlit conditions. The third generation night vision scope has zero sensitivity from 400 to 540 nm and high sensitivity in the NIR as shown in Fig. 4. A large fraction of the moonlight radiance falls into the former interval. Apparently, the trend in night vision devices is to make them relatively more sensitive in the NIR so that they can function just as well under moonless as moonlit conditions. Consequently the performance data for the third generation night vision scope were selected for testing purposes.

Under moonlit conditions the averages are less than the corresponding moonless values because the large difference in light intensity is nullified during the course of the calculations. The differences in the average L_s values among the three scopes is simply a metamerism effect due to the different spectral shapes of the sources. The averages under moonlit conditions are included to show that the relationship between the averages is similar to those under moonless conditions, and for future reference if needed.

The goal of the camouflage pattern is to have the dark green and brown regions of the pattern appear about the same in the NIR, with the light green regions significantly lighter. It is apparent from Figure 1 that, for the third generation scope under moonless conditions, the mean L_s values, 71.8 for Light Green 354 and 59.1 for Dark Green 355, are sufficiently far apart to provide a good contrast when viewed using the night vision device. However, the average minus two standard deviations, 66.7, for Light Green 354, is quite close to the average plus two standard deviations, 64.1, for Dark Green 355. Although the chance that this situation will arise is quite small, nevertheless, occasionally it will happen in production. Since the troublesome region for the Light Green 354 lies in the upper region of the acceptability band (See Table 2), it appears that an increase in the average for L_s will not only make it easier to meet the NIR requirements but will also provide greater contrast. A similar situation holds for the Dark Green 355 and Brown 356. In these cases the troublesome region lies in the lower limit of the acceptability channel. Consequently a decrease in the average values of L_s for these two shades should be beneficial.

Figure 3 shows that the average L_s values for Dark Green 355 and Brown 356 are close enough to be consolidated for moonlit as well as moonless conditions and for the Foreign, Second Generation, and Third Generation night vision devices.

Conclusion

For pass/fail acceptance, the ranges given in Table 5 are recommended. They are for use with the third generation night vision scope used under moonless conditions.

Table 5. Revised Ls Values for Pass/Fail Test

| | Light Green 354 | | Dark Green 355 | | Brown 356 | |
|------------------|-----------------|----------------|-----------------|----------------|-----------------|----------------|
| | <u>Computed</u> | <u>Revised</u> | <u>Computed</u> | <u>Revised</u> | <u>Computed</u> | <u>Revised</u> |
| Upper (+3 sigma) | 76.8 | 78.0 | 64.1 | 63.0 | 64.9 | 63.0 |
| Average | 71.8 | 73.0 | 59.1 | 58.0 | 59.7 | 58.0 |
| Lower (-3 sigma) | 66.7 | 68.0 | 54.1 | 53.0 | 54.5 | 53.0 |

The revised Ls values for Brown 356 were set equal to the revised Ls values for Dark Green 355.

This document reports research undertaken at the US Army Natick Research, Development and Engineering Center and has been assigned No. NATICK/TR-91039 in the series of reports approved for publication.

REFERENCES

1. Ramsley, A., and Yeomans, W., "Psychophysics of Modern Camouflage," U.S. Army Natick Research Development and Engineering Center, Natick, MA. 01760, Proceedings of the 1982 Army Science Conference, Vol. III, U.S. Military Academy, West Point, N.Y., 15-18 June 1982.
2. Military Specification Cloth, Camouflage Pattern, Woodland, Cotton, and Nylon. MIL-C-44031D, 22 August 1989, U.S. Army Natick Research, Development, and Engineering Center, Attn: STRNC-ES, Natick, MA 01760-5014Nylon.
3. Billmeyer, F. W. and Saltzman, M., "Principles of Color Technology," John Wiley and Sons, Second Edition, New York, NY, p. 63. 1981.
4. Decker, MAJ W. M., "Predicting the Performance of Night Vision Devices with a Simple Contrast Model," Center for Night Vision and Electro-Optics, AMSEL - NV - TR - 0062, Fort Belvoir, Va 22060 -5677, April 1988.

APPENDIX




Fig. 1. Lt. Green 354 vs. Dk. Green 355




Fig. 2. Lt. Green 354 vs. Brown 356





Fig. 3. Dk. Green 355 vs. Brown 356



**Fig. 4. Night Vision Scope Sensitivities
Normalized at 600 nm**